

**Abstract:**

The use of filler for the manufacture of paper and board products the air permeability of which does not substantially change as a function of the amount of filler, the filler being at  
5 least in part made up of cellulose or lignocellulose fibrils on which there have been deposited light-scattering material particles the proportion of which is 67 – 85 %, preferably approx. 70 – 82 %, of the weight of the filler.